Shenzhen Elegoo Technology Co.,Ltd.
Technical Data Sheet

Basic Introduction

Product Name: ELEGOO PETG-CF

Applicable Industry: Interior decorations, desktop accessories, outdoor equipments etc.

Manufacturer: Shenzhen Elegoo Technology Co.,Ltd.

Manufacturer Address: 101, No. 30, Dahe Industrial Zone, Guancheng Community, Guanhu Street, Longhua District, Shenzhen, Guangdong Province, China

Tel: +86-0755-21005141

Pin Code: 518000

Advantages

ELEGOO PETG CF significantly increases the stiffnes while retaining the toughness. This makes it resistant to bending and deformation under high loads, making it ideal for creating functional prototypes and load-bearing components. The addition of carbon fibre also gives printed parts a unique texture with a layer-masking effect, resulting in a smoother, glossier model surface.

Recommended Printing Settings

Drying Settings Before Printing: 60 °C, 8 h (Air Drying Oven)

Printing Temperature and Humidity: ≤ 20% RH (sealed with desiccant)

Storage Temperature and Humidity: ≤ 20% RH (sealed with desiccant)

Printer Type: Enclosed-frame, open-frame

Nozzle Material: Hardened steel

Nozzle Size: 0.4, 0.6, 0.8 mm

Plate Type: Textured PEI plate, smooth PEI plate or other plates

Plate Surface Pretreatment: Applying the glue

Nozzle Temperature: 240 - 270 °C

Bed Temperature: 65 - 75 °C

Printing Speed: < 220 mm/s

Chamber Temperature: 25 - 50 °C

Support Material: Self-generated support or PETG special support

Physical Properties

Subjects	Testing Methods	Data
Density	ρ = m / v	1.29 g/cm³
Saturated Water Absorption Rate	25 °C , 55% RH, Indoor air	0.35%
Melt Index	250 °C, 2.16 kg	10.3 ± 3.2 g/10 min
Glass Transition Temperature	DSC, 10 °C/min	69 °C
Crystallization Temperature	DSC, 10 °C/min	N / A
Melting Temperature	DSC, 10 °C/min	226 °C
Vicar Softening Temperature	ISO 306, GB/T 1633	83 °C
Heat Deflection Temperature 1	ISO 75, 1.80 MPa	70 °C
Heat Deflection Temperature 2	ISO 75, 0.45 MPa	74 °C

Mechanical Properties

Subjects	Testing Methods	Data
Tensile Strength (XY)	ISO 527, GB/T 1040	51 ± 8 MPa
Tensile Strength (Z)	ISO 527, GB/T 1040	38 ± 5 MPa
Young’s Modulus (XY)	ISO 527, GB/T 1040	2447 ± 118 MPa
Young's Modulus (Z)	ISO 527, GB/T 1040	1605 ± 158 MPa

Breaking Elongation Rate (XY)	ISO 527, GB/T 1040	9.6% ± 1.0%
Breaking Elongation Rate (Z)	ISO 527, GB/T 1040	7.5% ± 1.0%
Bending Strength (XY)	ISO 178, GB/T 9341	85 ± 2 MPa
Bending Strength (Z)	ISO 178, GB/T 9341	53 ± 4 MPa
Bending Modulus (XY)	ISO 178, GB/T 9341	3340 ± 21 MPa
Bending Modulus (Z)	ISO 178, GB/T 9341	2222 ± 33 MPa
Impact Strength (XY)	ISO 179, GB/T 1043	70.7 ± 6.2 kJ/m²
Impact Strength (Z)	ISO 179, GB/T 1043	14.6 ± 2.1 kJ/m²

Other Physical and Chemical Properties

Component: PETG and carbon fiber

Skin Irritation: No

Chemical stability: Stable at normal temperature

Resistance to Water: Resistant

Resistance to Oil and Grease: Resistant to most kinds of oil and grease

Resistance to Organic Solvent: Not resistant to some kinds of organic solvents

Resistance to Acid: Not resistant

Resistance to Alkali: Not resistant

Flammability: Yes

Odor During Printing: Odorless

Specimen Information

Size: Refer to the following pictures.

Nozzle Temperature: 255 ℃

Bed Temperature: 70 ℃


Printing Speed: 150 mm/s

Infill Density: 100%

Infill Pattern: Concentric pattern

Statements: The test specimens were printed under the key parameters mentioned above. Before testing, all specimens were annealed at 65 °C for 8 hours and then placed in an indoor environment at approximately 25 °C for 24 hours.


1. Tensile Testing



2. Bending Testing



3. Impact Testing



Disclaimer

The above properties data is obtained by ELEGOO through testing with standard samples, standard methods, and specific equipment, and is for reference and comparison only. The actual performance of 3D printed products depends not only on the characteristics used but also on many factors, such as the moisture absorption of the filaments, the printer, environmental conditions, model characteristics, printing parameters, etc.

When using the ELEGOO FDM 3D printing filaments, users are responsible for the legality, safety, and performance of the printing. ELEGOO is not responsible for the usage scenarios, or any damage or injury that occurs during using our filaments.